



ABSOLUTE DECKING
PREMIUM DECKING WITHOUT THE PREMIUM PRICE.

Technical Specification Prime Composite Decking


Dimensions:	Width: 132 mm Depth: 20 mm
Available Lengths:	3600 mm
Design / Finish:	Reversible - Woodgrain and Groove
Colour Options:	Teak, Ebony, Grey and Redwood
Installation Options:	Concealed Clip and Traditional Screw
FSC® Certification:	Licence Code: FSC-C007915
Other:	Colour Match Screws Available




Test	Method	Result
Slip Resistance:	BS 7962-2: 2002 + a1:2013	Dry Value: 52 Wet Value: 37 (Groove side only)
Reaction to Fire:	EN 13501-1: 2007 + A1:2009	Cfl-s1
Swelling:	EN 15534-4: 2014 Section 4.5.5	0.5% Depth, 0.1% Width, 0.1% Length
Water Absorption:	EN 15534-1: 2014 Section 8.3.1	0.5%
Indentation Resistance:	EN 15534-4:2014 Section 4.5.7 EN 15534-4:2014 Section 4.5.7	Brindell Hardness: 104 Mpa Rate of Elastic Recovery: 74%
Impact Resistance:	EN 15534-1: 2014 Section 7.1.1	Charpy Impact Strength: 4.4 kJ/m ²
Flexural Properties:	EN 15523-1 Section 4.5.2 EN 15534-4:2014 Annex A	3800 N
Bending Strength:	EN 15523-1:2014 Section 4.5.2 EN 15534:2014 Annex A	25.69 MPa
Modulus of Elasticity:	EN 15523-1:2014 Section 4.5.2 EN 15534-4:2014 Annex A	3406.80 MPa
Resistance to Artificial Weathering UV 2000 Hours:	ASTM D7032-17 Section 4.6 ASTM G154-16 Cycle 1	Exposure Time: 2000 Hours Grey Scale: 3-4
Freeze/Thaw Resistance:	ASTM D7032-17 Section 4.7 ASTM D6109-10	MOR: 36.7 MPa - Change: 3.2% MOE: 4386 MPa - Change: 0.9%
Density:	ASTM D792.13 Method A	Mean Value: 1.35g/cm ³



Grey



Ebony



Teak



Redwood



ABSOLUTE DECKING
PREMIUM DECKING WITHOUT THE PREMIUM PRICE.

01438 362 547 | info@builddeck.co.uk | www.builddeck.co.uk
Unit 4 Senate Place, Whitworth Road, Stevenage, SG1 4QS